



**Warminster Fiberglass**  
Water and Wastewater Treatment Products  
Keeping Americas' Water Clean

## **SECTION 11207 PARSHALL FLUMES**

### **PART 1 GENERAL**

#### **1.1 SECTION INCLUDES**

- A. Parshall flumes.

#### **1.2 RELATED SECTIONS**

- A. Section 03300 - Cast-In-Place Concrete.
- B. Section 11208 - Metering Manholes.

#### **1.3 REFERENCES**

- A. ASTM D 256 - Standard Test Methods for Determining the Pendulum Impact Resistance of Notched Specimens of Plastics.
- B. ASTM D 638 - Standard Test Method for Tensile Properties of Plastics.
- C. ASTM D 790 - Standard Test Methods for Flexural Properties of Unreinforced and Reinforced Plastics and Electrical Insulating Materials.
- D. ASTM D 2583 - Test Method for Indentation Hardness of Rigid Plastics by Means of a Barcol Impressor.

#### **1.4 SUBMITTALS**

- A. Submit under provisions of Section 01300.
- B. Product Data: Test results of fiberglass reinforced plastic laminate.
- C. Shop Drawings: Show:
  - 1. Critical dimensions, jointing and connections, fasteners and anchors.
  - 2. Materials of construction.
  - 3. Sizes, spacing, and locations of structural members, connections, attachments, openings, fasteners, and loads.
- D. Manufacturer's installation instructions.

#### **1.5 DELIVERY, STORAGE, AND HANDLING**

- A. Store products indoor and protect from construction traffic and damage.

Warminster Fiberglass  
P.O. Box 188  
Southampton PA 18966-0188  
725 County Line Road  
Phone: 215-953-1260 | Fax: 215-357-7893



**Warminster Fiberglass**  
Water and Wastewater Treatment Products  
Keeping Americas' Water Clean

## **PART 2 PRODUCTS**

### **2.1 MANUFACTURER**

**A.** Provide products manufactured by Warminster Fiberglass Company; P.O Box 188, Southampton PA 18966-0188; ASD. <http://www.warminsterfiberglass.com/> Tel. (215) 953-1260, Fax. (215) 357-7893.

**B.** Requests for substitution will be considered in accordance with provisions of Section 01600.

**C.** Substitutions: Not permitted.

### **2.2 PARSHALL FLUMES**

**A.** Material: Fiberglass reinforced plastic:

1. Tensile strength (ASTM D 638): 14,000 psi.
2. Flexural strength (ASTM D 790): 25,000 psi.
3. Flexural modulus (ASTM D 790): 1,000,000 psi.
4. Impact, Notched, Izod (ASTM D 256): 10 ft-lb/in.
5. Barcol hardness (resin-rich surface) (ASTM D 2583): 40, minimum, average.
6. Temperature limit: 150 degrees F.
7. Temperature limit: 200 degrees F.
8. Chemical resistance: Comply with ANSI/AWWA F101, Type II classification.

**B.** Construction: One-piece, fiberglass reinforced plastic, with integral stiffening ribs to make unit self-supporting and eliminate external bracing.

1. For flumes to be embedded in concrete, provide temporary internal bracing.
2. Make sizes 8-foot, 10-foot and 12-foot in two pieces for shipping.
3. Size(s): Indicated on the drawings.
4. Provide dual range (nested) flumes where indicated.
5. Provide factory assembled inner flume for field nesting in existing flume where indicated.
6. Provide custom height of flume where indicated.

**C.** Accessories:

1. Bushing for ultrasonic transponder mounting stand.
2. Integral stilling well, 8-inches diameter.
3. Integral stilling well, 10-inches diameter.
4. Integral stilling well, 12-inches diameter.
5. Integral stilling well, 14-inches diameter.
6. Staff gauge graduated in inches attached to inside wall of flume.
7. Staff gauge graduated in feet with 50 divisions per foot; attached to inside wall of flume.
8. Staff gauge graduated in feet, with 1-inch divisions per foot.
9. Staff gauge graduated in meters, with 1-millimeter divisions per meter.
10. Staff gauge graduated in GPM.
11. Staff gauge graduated in MGD.
12. Inlet and outlet transition caulking collars, and stub flanges.

Warminster Fiberglass  
P.O. Box 188  
Southampton PA 18966-0188  
725 County Line Road  
Phone: 215-953-1260 | Fax: 215-357-7893



**Warminster Fiberglass**  
Water and Wastewater Treatment Products  
Keeping Americas' Water Clean

13. Bubbler tube, molded in.
14. Drexelbrook track, molded in.
15. Special resin for temperature above 170 degrees F or chemical resistant service.

## **PART 3 EXECUTION**

### **3.1 EXAMINATION**

**A.** Verify that dimensions are correct and project conditions are suitable for installation. Do not proceed with installation until unsatisfactory conditions have been corrected.

### **3.2 INSTALLATION**

**A.** Install products in accordance with manufacturer's instructions.

**B.** Ensure that products are installed plumb and true, free of warp or twist, within tolerances specified by the manufacturer and as indicated in the contract documents.

**C.** Set flume at proper elevation in accordance with drawings.

**D.** Set floor of flume at inlet end level with flow and across flow. Set sidewalls plumb. Set top flanges level, each side.

**E.** Fasten flume securely to prevent flotation or twisting during placement of concrete.

**F.** Place concrete along sides and bottom of flume to ensure complete filling without voids and displacement of flume. Stage placement in alternating lifts, 1/3 height on each side of flume.

### **3.3 ADJUST AND CLEAN**

**A.** Clean surfaces in accordance with manufacturer's instructions.

**B.** Remove trash and debris, and leave the site in a clean condition.

## **END OF SECTION**

Warminster Fiberglass  
P.O. Box 188  
Southampton PA 18966-0188  
725 County Line Road  
Phone: 215-953-1260 | Fax: 215-357-7893